RG104 E-1 Box 121

1880

Weekly Report of Silver Purchases and Deposits Melted at United States Mint.

Date.	Assay No.	Name of Depositor.	Weight before Melting. OZ. DEC.	Weight after Melting. OZ. DEC.	Loss. OZ. DEC.	Loss per ct.	Gain. OZ. DEC.	Description of Bullion.
April 19th	179	G. C. Thompson	173 90	173 60	30	17		U. S. & For. Coin
	80	Do	46 55	45 55	1 00	2 13		Do
	1	Abraham Harris	62 60	62 20	40	63		Pl. Spoons, &c.
	2	T. J. Godwin & Bro.	193 80	193 05	75	39		For. Coin
	3	G. C. Thompson	611 40	567 15	44 25	7 24		Bar & Gold
20th	4	John Stuertz	117 60	117 30	30	25		Ring
21st	5	G. C. Thompson	161 80	153 20	8 60	5 31		Wtch Cases, Grs, Lake, Superior, &c.
	6	Sailer & Stevenson	1143 85	1143 73	12	01		"Platt" Bar
24th	7	G. C. Thompson	659 30	601 25	58 05	8 81		Bar & Gold
			3170 80	3057 03	113 77	3 59		

Transferred to Bullion fund during the week 41,706.50 Oz, Newark; 11,830.20 Oz, Platt; 51,704.45 Oz, St. Louis; 45,791.25 Oz, Omaha and 21,744.05 Oz, Pennsylvania Lead Company.

For week ending April 24th, 1880.

Date.	Assay No.	Name of Depositor.	Weight before Melting. OZ. DEC.	Weight after Melting. OZ. DEC.	Loss. OZ. DEC.	Loss per ct.	Gain. OZ. DEC.	Description of Bullion.
April 27th	188	G. C. Thompson	121 80	121 50	30	25		U. S. & For. Coin
	9	H. B. Chapman	173 10	172 90	20	12		For. & U. S. Coin
	90	Sailer & Stevenson	1019 05	1019 05				Bars, U. S. A. O. N. Y.
28th	1	I. Rosenbaum	359 00	337 85	21 15	5 89		Spoons, Forks, &c.
29th	2	G. C. Thompson	110 30	110 10	20	19		Spoons, Forks, &c.
	3	Thos. R. Lee	254 65	254 50	15	06		Bars
30th	4	Joel J. Baily & Co.	125 10	124 60	50	40		For. Coin
	5	Hastings & Co.	145 40	135 40	10 00	6 89		Skewings
			2308 40	2275 90	32 50	2 52		

Transferred to Bullion fund during the week 23,963.10 Oz, Boston & Colorado Bars; 17,874.35 Oz, Platt; 22,134.60 Oz, St. Louis; 102,020.75 Oz, Newark; 33,122.75 Oz, Omaha; 28,692.25 Oz, Pennsylvania Lead Company, and Foreign Coin which weighed before melting 2579.50 Oz, and 2577.25 after.

For week ending May 1st 1880.

Notes of Melter and Refiner.

The losses in melting the silver deposits are as follow:
4 Baser bars 7.06 %
2 Finer bars 03 %
4 Plate with a full loss of 1¾ %, but if No 191 be omitted, the loss is only moderate, at 0.36 %,
6 of coin, with a full loss of 0.58 %, but by omitting No 180, the fair average of .27 % is attained. No 191 must have had some quantity of base metal in it to lose nearly 6 %.

Jas H Booth
M & R.

J. Nobley Dunglison
Register

RG104 E-1 Box 121

Report of Silver Purchases
+ Deposits melted for
weeks ending :-
April 24th 1880
May 1st 1880

NARA RG104, Entry 1, Box 121

[Abstract:] Report of Silver Purchases & Deposits melted for weeks ending: -

April 24, 1880
May 1, 1880

Weekly Report of Silver Purchases and Deposits Melted at United States Mint.

[Please see original images for data table.]